

PVA-Fibre		HPF	
Item	Unit	Standard	3 year average
Titre	dtex	2,0 ± 0,25	2,05
Tenacity	cN/dtex	≥ 12,80	13,22
Young's Modulus	cN/dtex	≥ 290	311
Extension at Break	%	≤ 7	6,25
Cut Length	mm	4 or 5 or 6	4 or 5 or 6
Dispersability class	6 classes	1-2 from 6	1,33 from 6
Moisture Regain	%	5	5
Hot Water Solubility *)	%	≤ 2,00	0,61
DSC Onset **)	°C	-	106,9
DSC Max **)	°C	-	113,0
Sizing Agent	%	0,25 ± 0,15	0,25
Specific Gravity		1,29	1,29

**Packing:** 180kg net weight per bale (L: 550 mm, W: 600 mm, H: 1000 mm)

**Storage:** Inside warehouse at dry condition

\*) Hot Water Solubility Test at 90°C for 1 hour

\*\* ) DSC (Differential Scanning Calorimetry) showing temperature range for melting